

Nominale diameter	Gewicht/meter	Minimum breukkracht		
		1.770 N/mm ²	1.960 N/mm ²	2.160 N/mm ²
mm	kg/m	kN	kN	kN
8	0,27	40,4	44,7	49,1
9	0,34	51,1	56,6	62,3
10	0,42	63,1	69,8	76,8
11	0,51	76,3	84,5	93,0
12	0,60	90,8	101,0	111,0
13	0,71	107,0	118,0	130,0
14	0,82	124,0	137,0	151,0
15	0,94	142,0	157,0	173,0
16	1,07	161,0	179,0	197,0
17	1,21	182,0	202,0	222,0
18	1,36	204,0	226,0	249,0
19	1,51	228,0	252,0	277,0
20	1,67	252,0	279,0	307,0
21	1,84	278,0	308,0	339,0
22	2,02	305,0	338,0	372,0
23	2,21	334,0	369,0	406,0
24	2,41	363,0	402,0	442,0
25	2,61	394,0	436,0	480,0
26	2,83	426,0	472,0	519,0
27	3,05	460,0	509,0	560,0
28	3,28	494,0	547,0	602,0
29	3,52	530,0	587,0	646,0
30	3,76	568,0	628,0	691,0
31	4,02	606,0	671,0	738,0
32	4,28	646,0	715,0	787,0
33	4,55	687,0	760,0	836,0
34	4,83	729,0	807,0	888,0
35	5,12	772,0	855,0	941,0
36	5,42	817,0	905,0	996,0
37	5,73	863,0	956,0	1052,0
38	6,04	911,0	1008,0	1109,0
39	6,36	959,0	1062,0	1168,0
40	6,69	1009,0	1117,0	1229,0
41	7,03	1060,0	1174,0	1291,0
42	7,38	1112,0	1232,0	1355,0
43	7,73	1166,0	1291,0	1420,0
44	8,10	1221,0	1352,0	1487,0
45	8,47	1277,0	1414,0	1555,0
46	8,85	1334,0	1478,0	1626,0
47	9,24	1393,0	1543,0	1697,0
48	9,64	1453,0	1609,0	1770,0
49	10,00	1514,0	1677,0	1845,0
50	10,50	1576,0	1746,0	1921,0
51	10,90	1640,0	1816,0	1998,0
52	11,30	1705,0	1888,0	2076,0
53	11,70	1771,0	1961,0	2157,0
54	12,20	1839,0	2036,0	2240,0
55	12,70	1908,0	2112,0	2323,0
56	13,10	1978,0	2190,0	2409,0
57	13,60	2049,0	2269,0	2496,0
58	14,10	2121,0	2349,0	2583,0
59	14,60	2195,0	2431,0	2674,0
60	15,10	2270,0	2514,0	2765,0
62	16,10	2424,0	2684,0	2952,0
64	17,10	2583,0	2860,0	3146,0