

Nominale diameter	Gewicht/meter	Minimum breekkracht		
		1.770 N/mm ²	1.960 N/mm ²	2.160 N/mm ²
mm	kg/m	kN	kN	kN
8	0,24	37,4	41,4	45,5
9	0,31	47,3	52,4	57,6
10	0,38	58,4	64,7	71,2
11	0,46	70,6	78,2	86,0
12	0,55	84,1	93,1	102,0
13	0,64	98,7	109,0	120,0
14	0,75	114,0	127,0	140,0
15	0,86	131,0	145,0	160,0
16	0,97	149,0	166,0	183,0
17	1,10	169,0	187,0	206,0
18	1,23	189,0	209,0	230,0
19	1,37	211,0	233,0	256,0
20	1,52	234,0	259,0	285,0
21	1,68	257,0	285,0	314,0
22	1,84	283,0	313,0	344,0
23	2,01	309,0	342,0	376,0
24	2,19	336,0	372,0	409,0
25	2,38	365,0	404,0	444,0
26	2,57	395,0	437,0	481,0
27	2,77	426,0	471,0	518,0
28	2,98	458,0	507,0	558,0
29	3,20	491,0	544,0	598,0
30	3,42	525,0	582,0	640,0
31	3,65	561,0	621,0	683,0
32	3,89	598,0	662,0	728,0
33	4,14	636,0	704,0	786,0
34	4,40	675,0	747,0	822,0
35	4,66	715,0	792,0	860,0
36	4,93	757,0	838,0	900,0
37	5,21	799,0	885,0	942,0
38	5,49	843,0	934,0	987,0
39	5,78	888,0	983,0	1034,0
40	6,08	934,0	1034,0	1081,0
41	6,39	981,0	1087,0	1137,0
42	6,71	1030,0	1140,0	1196,0
43	7,03	1080,0	1195,0	1254,0
44	7,36	1130,0	1252,0	1315,0
45	7,70	1182,0	1309,0	1377,0
46	8,05	1235,0	1368,0	1440,0
47	8,40	1290,0	1428,0	1505,0
48	8,76	1345,0	1490,0	1571,0
49	9,13	1402,0	1552,0	1639,0
50	9,51	1460,0	1616,0	1707,0
51	9,89	1519,0	1682,0	1778,0
52	10,30	1579,0	1748,0	1850,0
53	10,70	1640,0	1816,0	1923,0
54	11,10	1703,0	1885,0	1998,0
55	11,50	1766,0	1956,0	2074,0
56	11,90	1831,0	2028,0	2152,0
57	12,40	1897,0	2101,0	2231,0
58	12,80	1964,0	2175,0	2311,0
59	13,20	2032,0	2251,0	2393,0
60	13,70	2102,0	2328,0	2476,0
62	14,60	2244,0	2485,0	2661,0
64	15,60	2392,0	2648,0	2834,0