

DIN 3064**6 x 37FC (TOUWKERN)**

Nominale diameter	Gewicht/meter	Minimum breukkracht 1.770 N/mm ²		Minimum breukkracht 1.960 N/mm ²	
mm	kg/m	kN	kg	kN	kg
5	8,70	13,1	1330,0	14,5	1478,1
6	12,50	18,8	1910,0	20,8	2120,3
7	17,00	25,6	2600,0	28,3	2884,8
8	22,10	33,4	3400,0	37,0	3771,7
9	28,00	42,3	4300,0	46,8	4770,6
10	34,60	52,2	5310,0	57,8	5891,9
11	41,90	63,2	6420,0	70,0	7135,6
12	49,80	75,2	7640,0	83,3	8491,3
13	58,50	88,2	8970,0	97,7	9959,2
14	67,80	102,0	10400,0	113,0	11518,9
16	88,60	134,0	13600,0	148,0	15086,6
18	112,00	169,0	17200,0	187,0	19062,2
20	138,00	209,0	21200,0	231,0	23547,4
22	167,00	253,0	25700,0	280,0	28542,3
24	199,00	301,0	30600,0	333,0	33945,0
26	234,00	353,0	35900,0	391,0	39857,3
28	271,00	409,0	41600,0	453,0	46177,4
32	354,00	535,0	54300,0	592,0	60346,6
36	448,00	677,0	68800,0	749,0	76350,7
40	554,00	835,0	84900,0	925,0	94291,5
44	670,00	1011,0	103000,0	1120,0	114169,2
48	797,00	1200,0	122000,0	1330,0	135575,9
50	865,00	1310,0	133000,0	1450,0	147808,4